

Product range

STRUCTURAL BEARINGS

Guarantee of high quality for the construction industry



Due to the combined effects of permanent static loads (dead load), live dynamic loads (e.g. wind) and concentrated restraints (e.g. due to temperature changes, creep, tolerances or settlements) relative movement within structures must always be considered. Without appropriate elastomeric bearings these influences will lead to damages. Beside cracks and spalling in concrete members, extensive deterioration can occur within adjacent structural members. The repair of those damages has significant time & cost implications.

Structural bearings concentrate high loads towards to the centre and can accommodate movements and rotations (angle of distortion) at the same time. Due to their low coefficient of friction, our sliding bearings are able to compensate large deformations and movements.




UNREINFORCED BEARINGS					
	Bearing name	Bearing type	Thickness [mm]	Compressive stress	Approval
	Compact Bearing S 65	Unreinforced deformation bearing	5*	$\sigma_{R,d} = 14 \text{ N/mm}^2$	Approval No. Z-16.32-474, issued by DIBt Berlin
			8*		
			10		
			15		
			20		
			25		
	Compact Bearing S 70	Unreinforced deformation bearing	5*	$\sigma_{R,d} = 21 \text{ N/mm}^2$	Approval No. Z-16.32-477, issued by DIBt Berlin
			8*		
			10		
			15		
			20		
	Compact Bearing CR 2000	Unreinforced profiled deformation bearing	11	max. $\sigma_K = 20 \text{ N/mm}^2$	Approval applied
			16		
			21		
	bi-Trapez Bearing®	Unreinforced deformation for impact sound insulation	5*	Shape depending (max. $\sigma_{R,d} = 17,4 \text{ N/mm}^2$)	Approval No. Z-16.32-455, issued by DIBt Berlin
			10		
			15		
			20		
	Cigular® Slab Bearing	Deformation bearing with low shear resistance	10	$\sigma_{R,d} = 1,5 \text{ N/mm}^2$	Approval No. Z-16.32-479, issued by DIBt Berlin
	Cigular® Slab Bearing EcoLine	Deformation bearing with low shear resistance	10	$\sigma_{R,d} = 1,5 \text{ N/mm}^2$	Approval No. Z-16.32-479, issued by DIBt Berlin

* without official approval



REINFORCED BEARINGS

	Bearing name	Bearing type	Thickness [mm]	Compressive stress	Approval
	Perforated™ Bearing, Type Z	Steel-reinforced perforated bearing	15	max. $\sigma_K = 25 \text{ N/mm}^2$	Approval applied
			24		
			33		
			42		
			51		
	Sandwich Bearing Q	Steel-reinforced bearing	10	max. $\sigma_{R,d} = 28 \text{ N/mm}^2$	Approval No. Z-16.33-480, issued by DIBt Berlin
			20		
			30		
			40		

SLIDING BEARINGS

	Bearing name	Bearing type	Thickness [mm]	Compressive stress	Approval
	Ciparall® Sliding Bearing	Reinforced point sliding bearing	11	max. $\sigma_K = 15 \text{ N/mm}^2$	Type GFK Approval No. Z-16.2-518, issued by DIBt Berlin
			14		
			20		
			30		
			40		
	Perforated™ Sliding Bearing, Type Z	Reinforced point sliding bearing	15	max. $\sigma_K = 25 \text{ N/mm}^2$	Approval applied According to DIBt official test certificate valid till approval issued
			25		
			34		
			42		
			51		
	Civalit® Sliding Bearing	Point / strip sliding bearing	11	max. $\sigma_K = 15 \text{ N/mm}^2$	Approval applied According to DIBt official test certificate valid till approval issued

SPECIAL PRODUCTS

	Bearing name	Bearing type	Thickness [mm]	Compressive stress	Approval
	Compact Core Bearing	Unreinforced heavy-duty bearing for thermal separation of steel structures	5	max. $\sigma_K = 30 \text{ N/mm}^2$	Approval applied
			10		
			15		
			20		
	Cipolon® Edge Protection	Edge protection, sealing	7	Unnecessary	Unnecessary



Am Knübel 2 - 4
31020 Salzhemmendorf | Germany

Tel. + 49 51 53 - 94 00-0
Fax + 49 51 53 - 94 00-49

info@calenberg-ingenieure.de
www.calenberg-ingenieure.de

A LISEGA Group Company

04 February 2022 | 7. edition | ©Calenberg Ingenieure GmbH | Subject to change



The contents of the publication in the result of many years of research an experience gained in application technology. All information is given in good faith; it does not represent a guarantee with respect to characteristics an does not exempt the user from testing the suitability of products and from ascertaining that the industrial property rights of third parties are not violated. No liability whatsoever will be accepted for damage – regardless of its nature and its legal basis – arising from advice given in this publication. This does not apply in the event that we or our legal representatives or our management are found guilty of having acted with intent or gross negligence. The exclusion of liability applies also to the personal liability of or legal representatives and employed in performing our obligations.